

Proseries Flexiseal FC

Polyurethane Adhesive/Sealant

Description

Selleys Proseries Flexiseal FC is a non-slumping polyurethane based adhesive and sealant. It has excellent adhesive properties to most common building substrates, weatherproof and suitable for indoor and outdoor applications. It is available as a 600mL sausage in a range of colours.

Uses

Flexiseal FC is a multipurpose, high performance, sealant and elastic adhesive. It is ideal for bonding common building materials and sealing construction joints in vertical and horizontal applications including:

- External wall and cladding joints
- Weatherproofing joints between brickwork, masonry, wood concrete or metal frames.
- Joints in walls, balconies, around window or door frames.
- Joints in bridge and balcony parapets
- Retaining walls
- Roofing.
- Acoustic rated walls
- As an adhesive for indoor and outdoor bonding of window sills, thresholds, stair steps, skirting boards, base boards, crash protections boards, covering boards, prefabricated elements,...

Features/Advantages

- High flexibility with +/-25% joint movement capability
- Excellent resistance to aging and weathering
- No shrinkage during curing
- Excellent adhesion on common building materials such as concrete, masonry, brick, ceramic tile, metals, soft wood, hardwood and some plastics
- Certified according to ISO11600/F/25HM
- Will not degrade acoustic walls that meet the BCA requirements

Instructions for Use/Application Instructions

For Sealing purposes:

The following should only be used as a guide and the installer should apply all Australian Standards, BCA/NZBC requirements, and best practices when installing.

- Surface must be clean, dry and free from oil, grease, release agents, dust and loose material.
- Install backing rod to correct depth apply masking tape as required.
- Cut the end of the sausage and insert into a Selleys sausage gun.
- Extrude sealant into the joint such that it is in full contact with the sides of the joint. Avoid overlapping of sealant to eliminate entrapment of air.
- Smooth sealant with spatula forcing the sealant into the joint for better contact with the sides.
- Painting with waterbased paints is possible after curing. If solvent based paints are used; prime first with waterbased primer.

Priming

Selleys *Flexiseal FC* generally has good adhesion properties without priming to common building materials indicated. In some instances a primer may be required and a pre-test to ensure suitable adhesion is recommended.

Joint & sealant dimensions

The optimum width to depth ratio for joint sealing is 2:1.

Minimum joint width and depth is 6mm.

For joint widths up to 12mm, use a width to depth ratio of 1:1

For joint widths greater than 12mm, use a width to depth ratio of 2:1

Notes:

- Wider joints can accommodate more total movement than narrow joints.
- Always install suitable diameter backing-rod (polyethylene or polyurethane foam rod) in joints to control sealant depth and ensure free movement of sealant in joints.
- Sealant must adhere to sides of the joints only and NOT to the back, so that it is free to stretch.

For adhesive purposes ensure surfaces are clean, dry and free from oil, grease, release agents, dust and loose material. Apply *Flexiseal FC* in spots or beads on the prepared surfaces then firmly press the parts together. If necessary, use suitable fixing until the adhesive has cured.

Estimation of lineal coverage per Flexiseal sausage

Joint Width (mm)	Joint Depth (mm)	Litre per lineal meter	Meters of Coverage
6	6	0.036	16.7
8	8	0.064	9.4
10	10	0.100	6
12	12	0.140	4.2
14	7	0.098	6.3
16	8	0.128	4.7
18	9	0.162	3.7
20	10	0.200	3
22	11	0.242	2.5
24	12	0.288	2.1
26	13	0.338	1.8
28	14	0.392	1.5
30	15	0.450	1.3
40	20	0.800	0.8

Technical Data/Properties

Contact Selleys before using this data for the setting of specifications.

Property	Typical Result
Colour	Grey, Black, White
Density	1.29
Technology	Polyurethane
Application Temperature	5 – 35°C
Shelf Life	12 months
Shore A Hardness (DIN 53505)	40 - 45
Joint Movement Capability	+/-25%
Tack free time at 23°C and 50% r.h	55 – 65 minutes
Curing at 23°C and 50% r.h.	≥ 2,5 mm/24h
Elongation at Break (DIN 53504)	>550%
Elastic Modulus @ 100% (DIN 52455)	0.8N/mm ²
Tensile Strength (DIN 53504)	>1.8N/mm ²
Service Temperature	- 40°C / +90°C with brief points at 120°C

Important Notes/Limitations

- Do not apply if air or substrate surface temperature is below 5°C.
- Requires atmospheric moisture to cure.
- Not recommended for continuous submersion or below water line use.
- Do not apply in the presence of curing silicone sealants as cure may be affected.
- Avoid contact with alcohol and other solvent cleaners during cure as cure will be affected.
- Application to substrates with high moisture can cause bubbling within the sealant.
- Do not use for structural or general glazing.
- Avoid air entrapment while applying sealant
- May affect drying of alkyd /oil based paints
- White sealant may yellow slightly with age and exposure to the sun.
- Do not store product above 30°C.

Storage

Store unopened sausages below 30°C in a cool dry place away from direct sunlight. Unopened sausages can be stored for 12 months from the date of manufacture. Opened sausages may skin and form a lump near the opening. Discard any lumps or skin and remaining product can be used.

Safety

Classified as HAZARDOUS - contains Isocyanates

Wear gloves and safety glasses when using.

Not classified as Dangerous Goods.

Refer to Safety Data Sheet for more detailed information.

Clean up

Spills and tools can be cleaned up with Mineral Turps before product cures. Cured product can only be removed mechanically.

Disclaimer

All information contained in this Product Information Sheet is as accurate and up-to-date as possible. Products can be expected to perform as indicated in this Sheet, so long as application procedures are followed as recommended. Notwithstanding the above, any recommendations made by Selleys or its distributors in relation to this or other products is to be taken as advice only. Selleys makes no representations or warranties that this product will be suitable for use. Subject to any applicable legislation which cannot be excluded (such as the Australian Consumer Law), Selleys takes no responsibility and will not be liable for any failure in performance of this product or any losses, damages, or injuries (consequential or otherwise) arising from the storage, mixing, application or other use of this product or for any representations made by you about the product which have not been approved in writing by Selleys. The buyer assumes all risk and responsibility for the use of this product.

© 2013 Selleys Pty Limited

Selleys – a division of DuluxGroup Australia Pty Ltd

1 Gow Street, Padstow, NSW 2211

1300 555 205 (Australia)

0800 735 539 (New Zealand)